Analysis Report 41407/E
Translation of Analysis Report 41407, Made on 2004-08-11

Required Tests:

NF P92-501 (1995) - “Exposure to radiant heat”
French Decree from 21st November 2002 - Reaction to fire tests on interior material

Sampling by:

Korbel

Identification Number:

T406359, T406360

Information Given By Client:

Vertical salts in PVC - Thickness 0.7mm, 7114/89 - Brown - Thickness 0.7mm, 7111/89 - Beige - Thickness 0.7mm

Date of Receipt:

07/01/2004

Reference:

Vertcial Slats in PVC - Thickness 0.7mm
T406359 - 7114/89 - Brown - Thickness 0.7mm
T406360 - 7111/89 - Beige - Thickness 0.7mm

NF P92-501 (1995) - "Exposure to radiant heat"
French Decree from 21 November 2002 - Reaction to fire tests on interior materials

End of Tests: 9 August 2004

The test specimens have not been cleaned nor submitted to an accelerated aging procedure.

Conditioning

Minimum 7 days at (23 ± 2)°C and (50 ± 5) % RH

or

Unitil constant mass is achieved

Specimen width: 9cm

Each Test specimen is composed of 3 slats with a width of 9cm.

Specimen	406359		406360		Average
Ignition (s)					
Face ti(f)	*	*	*	42	
Back ti(b)	*	*	*	*	
Total Flame Time (T)	0	0	0	12	
Sum of flame heights H (cm)	0	0	0	3	
Max Flame Height (cm)	0	0	0	3	
$q = \frac{100H}{ti\sqrt{T}}$	0	0	0	2.1	0.5

ti : lowest value ti(f) / ti(b) * no ignition

Classification :

q< 2.5	M1
q< 15	M2
q< 50	M3
Propagation < 2mm/s	M4

Conclusion : **M1**

Performed under accredidation in the fire laboratory under the responsibility of Pros Van Hoeyland

Approved Supplier:

CI/SfB 1976 reference by SfB Agency			
	(76.7)	X	